



### PRODUCT PROFILE

#### DESCRIPTION

**RAINSTOPPER® 2000W CLEAR** is a combination of a silicone emulsion with a reactive silane producing a penetrating concrete and masonry sealer and water repellent.

#### FEATURES

- A Viscosity Comparable to Water
- One-Component Ready-To-Use; No Catalyst Required
- Reactive Silane to Chemically Link To the Substrate for Permanent Protection

#### BENEFITS

- VOC Compliant
- Protects Against Moisture Chemical and Salts
- Breathable; Allows Moisture Vapor to Pass Thru From Interior

#### RECOMMENDED PRIMERS/SUBSTRATES

Brick, Masonry, Stone, Aggregate, Gravel, Precast Concrete, Architectural Concrete, Stucco, and Synthetic Stone

### PRODUCT APPLICATION

#### APPLICATION EQUIPMENT

RAINSTOPPER® 2000W CLEAR may be roller or spray applied. A low pressure spray until (20-25 pounds per square inch) or Hudson sprayer is recommended.

#### GENERAL/SURFACE PREPARATION

Before application, be sure the surface is clean and free of environmental dirt, efflorescence, form oils, curing compounds or any other foreign matter that can affect the penetration of RAIN STOPPER® 2000W Clear. Surface to be treated should be uniformly dry. Surface cleanliness can be tested by putting a drop of water on surface to be coated. If water is rapidly absorbed, substrate is ready for application. If water sits on surface, or looks like an oily spot, more cleaning is required.

#### APPLICATION RATE

Application rate will vary dependent upon porosity. For brick, masonry, stone, aggregate, and stucco, estimate 75 to 100 square feet per gallon of product for sealing applications.

For precast concrete, architectural concrete, and synthetic stone, estimate 100 to 125 square feet per gallon of product.

For priming, coverage per gallon of concentrate is approximately double-sealing operations.

#### APPLICATION

RAINSTOPPER® 2000W Clear is ready-to-use. Mix container thoroughly before use. For application, achieve a flooding condition with rundown. Multiple applications should be wet on wet to ensure penetration of the sealer.

#### CLEAN-UP

Clean up wet overspray on glass, metal or painted surfaces immediately with water; RAINSTOPPER® 2000W Clear adheres tightly to surfaces when cured. Spray-on or roll equipment must be cleaned up with water immediately while wet.

### BEST PERFORMANCE

#### IMPORTANT STEPS

- Masonry should be cured a minimum of 28 days before application.
- Rain or snow is not imminent.
- Surface should be free of foreign matter and not frozen.
- Keep containers sealed.
- RAINSTOPPER® 2000W Clear is for above-grade only.
- Allow to cure under ideal conditions for a minimum of 72 hours if an oil based system is to be applied. Environmental temperatures should be between 45 ° F and 100° F (7.D-37.7 °C).
- Do NOT store near excessive heat or flame.
- During application use splash goggles, rubber gloves, protective apron and vapor respirator.
- Storage: Up to 12 months in sealed containers stored at 45 ° F to 100° F.
- TEX-COTE LLC does NOT promote or recommend coating the sealant joints, nor is the sealant compound an approved substrate.
- Do NOT store near excessive heat or flame.
- NOT designed as waterproof system to meet severe wind driven rain conditions.
- During application use splash goggles, rubber gloves, protective apron and vapor respirator.

### TECHNICAL DATA

#### PHYSICAL PROPERTY

#### TYPICAL RESULT

Appearance of Dry Film

Milky Liquid

-

Silane/Siloxane Emulsion

Active Content

10% (± 5)

Density

8.2 lbs

#### PHYSICAL PROPERTY

#### TYPICAL RESULT

Viscosity

25 cps

VOC (grams/liters minus water)

<120 g/L

Dry Time

30 Minutes

Cure Time

12 Hours

ORDER INFORMATION

PACKAGING	Available in one (1), five (5), thirty (30), and fifty-five (55) gallon containers.
COVERAGE RATES	Application rate will vary dependent upon porosity. For brick, masonry, stone, aggregate and stucco, estimate 75-100 square feet per gallon.
SHELF LIFE	12-Month Shelf Life under proper conditions: <ul style="list-style-type: none"><li>• Containers are sealed, upright and airtight in a dry place.</li><li>• Maintain temperature of 45°F to 100°F (7°C to 37.7°C); AVOID FREEZING.</li><li>• Skins formed on surface of material must be removed prior to moving containers or mixing.</li></ul>

SAFETY

WARNING	<ul style="list-style-type: none"><li>• Use with adequate ventilation.</li><li>• View Material Safety Data Sheet (MSDS) before using material.</li><li>• Keep out of reach of children.</li></ul>
VOC COMPLIANCE	<p>All TEX-COTE® products comply with federal Volatile Organic Compound (VOC) rules and regulations.</p> <p>Please contact your nearest TEX-COTE LLC office for assistance on the local and state VOC compliance in the area of intended use.</p>

WARRANTY

Upon completion of the application of the coating in accordance with the manufacturer's recommendations, TEX-COTE LLC will extend its limited commercial warranty for product replacement as a result of a defect in the material. The manufacturer must be notified prior to the application of the coating and the application must be in compliance with the manufacturer's recommendations for installation. TEX-COTE LLC shall have no obligation to contribute to or otherwise participate in labor or cost associated with effecting repairs. Specimen copy of material warranty is available upon request.

Corporate HQ & East Coast Facility	2422 E. 15th St., Panama City, FL 32405   800-454-0340   850-769-0347   Fax 850-913-8619
South Florida Sales Office	7000 W. Palmetto Park Rd., Ste 210-W14, Boca Raton, FL 33433   954-581-0771   Fax 954-581-9516
West Coast Facility	417 E. Weber Ave., Compton, CA 90222   323-233-3111   Fax 310-438-2873