



## Architectural & Protective Coatings

# TEX•COTE® 300 BRIDGE AND HIGHWAY PAINT AND HEAVY STAIN

### DESCRIPTION

TEX •COTE® 300 BRIDGE AND HIGHWAY PAINT AND HEAVY STAIN is an acrylic polymer stain formulated for use on concrete / masonry surfaces.

TEX •COTE® BRIDGE AND HIGHWAY PAINT AND HEAVY STAIN features rapid drying, good adhesion, moisture resistance and flexibility. These features

help compensate for temperature variations experienced in various climates.

### FEATURES

Waterbased, low VOC coating. Fast dry

### BENEFITS

Very good color retention, even in deep tones

### RECOMMENDED OVER

Poured concrete, precast concrete and other manufacturer approved surfaces.

### APPLICATION

**Application Equipment:** Spray On Application: Use airless spray equipment , tip size 0.17-0.19 TEX •COTE® application manual available upon request. Roll On Application: Overall appearance depends on application technique. Mock-up sample for architect/owner approval is recommended. Short, medium or long nap rollers (3/8 "-3/4 ") may be used for standard application.

**Surface Preparation:** All surfaces must be sound, clean and dry. Such surface contaminants as dust, dirt, mildew, form oils, curing compounds and loose substrates should be thoroughly removed. Test the wall for stain acceptability prior to application of stain. This can be done by spraying the wall with water. If the water soaks into the wall, the wall is properly prepared and can be stained when dry. If the water beads up and is repelled, the wall requires further cleaning prior to application of the stain.

Sack and patch should be completed prior to stain application. If undesirable, large cracks, holes or voids must be filled with cement patching compound which uses a bonding agent. patching compound finish texture to match existing adjacent surfaces. preparation, degreasing, and etching is

**Application of stain:** A sample wall is recommended for field approval by the architect, manufacturer 's representative, and contractor .

Provide a properly prepared surface for all stain systems, material coverage can vary due to surface porosity and texture.

**Note:** Due to differences experienced in spraying TEX •COTE® materials, TCA shall be contacted if the contractor has never applied TEX•COTE® products to discuss proper spray techniques. .

#### Recommended Application Rate: Concrete /Masonry smooth surface

1 coat 100-150 sq ft per gallon OR 2 coats. 200– 300 square feet per gallon per coat. Depending on surface porosity and color selected.

When rolling, apply first with vertical strokes, then crossroll for even film and desired appearance.

**Maintenance:** No particular maintenance is required. However, should any of the product become soiled, simply clean with light water pressure and mild detergent.

**Clean Up:** Use water for cleaning wet material; methyl ethyl ketone (MEK ) for dry material.

Refer to SDS before use.

### Best Performance

TEX •COTE® 300 BRIDGE AND HIGHWAY PAINT AND HEAVY STAIN shall be applied under the following conditions:

1. Rain is not imminent and surfaces are not damp or frozen.
2. Temperature is at least 45°F and rising up to no more than 100°F (7° C—38°C )
3. TCA is not responsible for stain over sealants/caulked joints. TCA accepts no responsibility for the performance of its stains on a surface that is not approved.
4. Incompatible substrate release agents, form oils, and any foreign matter shall be removed.
5. Material use is above grade only. Do not use below grade.
6. Product must be used within 12 months when stored and handled as specified by manufacturer.

## TECHNICAL DATA

**Table 1 Applicable Standards**

American Society for Testing Materials (ASTM):

ASTM D2243—Freeze—Thaw Resistance of water borne material—pass

ASTM E96-95—Standard Test Methods for Water Vapor Transmission of Materials—9.7 Perms

FTM 141: Fungus Growth Resistance—Pass, No Growth

ASTM D6904—Wind Driven Rain: — 0.0g of weight gain

**Table 2 Technical Properties**

Test Property	Typical Result
Solids % by weight	51%
Solids % by volume	36%
Weight per gallon, lbs.	11.0
VOC, grams/liter	100 max.

## ORDER INFORMATION

**Colors:** Available in standard TEX • COTE® colors and custom colors. Deep tones subject to upcharge.

**Shelf Life:** Twelve month shelf life based on the following:

- Containers shall be stored upright and airtight in a dry place.
- Maintain air temperature of 45°F to

100°F (7°C to 38°C) Do not store outside or exposed to direct sunlight which can dry materials and cause them to excessively skin .

- Skins formed on surface of material must be removed prior to moving containers or mixing.

## SAFETY

**Warning:** TEX • COTE® 300 BRIDGE AND HIGHWAY PAINT AND HEAVY STAIN Use in well ventilated areas.

**First Aid:** If you experience difficulty in breathing, leave area to obtain fresh air. If difficulty continues, seek medical attention. In case of eye contact, flush immediately with large quantities of water for at least 15 minutes. Seek medical attention if blurring or redness continues. Caution: This product, in liquid form, contains ethylene glycol which will cause serious illness or death if swallowed, or if large quantities are absorbed into body. In liquid form, keep away from heat sources and children. If swallowed, do not induce vomiting. Call physician at once.

diately with large quantities of water for at least 15 minutes. Seek medical attention if blurring or redness continues. Caution: This product, in liquid form, contains ethylene glycol which will cause serious illness or death if swallowed, or if large quantities are absorbed into body. In liquid form, keep away from heat sources and children. If swallowed, do

not induce vomiting. Call physician at once.

## WARRANTY

Upon completion of application of coating in accordance with the manufacturer's recommendations, Textured Coatings of America, Inc. will extend its limited commercial warranty for product replacement as a result of defect in the material. The manufacturer must be notified prior to the application of the coating and the application must be in compliance with the manufacturer's recommendations for installation. Textured Coatings of America, Inc. shall have no obligation to contribute to or otherwise participate in labor or cost associated with effecting repairs. Specimen copy of material warranty available upon request.



**CORPORATE OFFICES & EASTERN PLANT**

2422 East 15th Street Panama City, Florida 32405  
Tel: (850) 769-0347 Fax: (850) 913-8619

**COMMERCIAL SALES OFFICE**  
4101 Ravenswood Road, Suite 218,  
FT. Lauderdale, Florida 33312  
Tel: (954) 581-0771 Fax: (954) 581-9516

**WESTERN PLANT**  
5950 S. Avalon Blvd.  
Los Angeles, California 90003  
Tel: (323) 233-3111 Fax: (323) 232-1071